

TECHNICAL DATA FINITEXT[®] ARY 3500 CI

Trade Name: FINITEXT[®]

Type: Yarn with outside braiding

Raw material: Expanded graphite yarn and inkonel (Cr20 Ni80, 0,1mm)

Properties		Range	Test method
Yarn Type	Expanded graphite with cotton fiber		
Inconel contents	%	18--20	
Yarn count	tex	3500+10%	F.I. 1883

It is acceptable at every 10 meters along the yarn 2 to 3 cm of the braiding to be doubled.

Reinforced: copper, brass, stainless steel, inkonel wire and other – on requested

Application: Because of its excellent thermoresistance and high insulation ability it is recommended for production of ropes, cords and etc with good thermoresistance. It is recommended for substitution of asbestos materials.

Health Hazard Information: Such are not being ascertained.